



Use of Laponite® as an antistatic agent

Fields of use

There are two areas where Laponite® is used as an antistatic agent:

- To produce antistatic finished articles- such as paper, glass and polymer films. Laponite® is usually applied as a coating to a material in order to produce an antistatic film on the surface of a product.
- To act as a process aid- processes that involve handling of small particles in dry environments can be liable to be affected by a build-up of static electricity. Laponite® can be added into such a system to dissipate this static charge. The finished product from the process will not normally be classified as an antistatic material.

Grades

All Laponite® types are electrically conductive and can be used to develop antistatic effects. Laponite® sol grades are particularly useful for using to make antistatic treatments as they can be prepared as concentrated low viscosity dispersions that are easy to apply.

Recommended grades are Laponite® RDS, Laponite® JS, Laponite® S482 and Laponite® SL25.

Use level

- To make an antistatic surface treatment- typical use level is at a coat weight of 1g.m^{-2} to 5g.m^{-2} .
- As an antistatic process aid- typical use level is from 0.1% to 1.0% of the total dry mass of material that is being handled by the process.

Applications/ substrates where Laponite® can be used as an antistatic agent include:

Thermal printing media, paper and polymer film	Polymeric fibres and materials, such as non-wovens
Packaging materials for electronics	Speciality printing papers
Electrographic paper	Antistatic abrasive base paper
Photographic media	Processing of paper fibre
Polymer packaging film	Processing of leather
Glass sheets and fibres	Processing of seeds

For more information- contact the Laponite team on help@laponite.com

Laponite is a registered trademark of Rockwood Additives Limited. All information here is given in good faith but without warranty or guarantee of any kind whatsoever, whether implied or expressed. Freedom from patent rights must not be assumed. This leaflet does not form part of the conditions of sale, is of a general nature and should not be used as the basis of a specification.

Southern Clay Products, Inc., Rockwood Additives Limited and Rockwood Clay Additives GmbH are wholly owned subsidiaries of Rockwood Specialties Group, Inc.

Rockwood Additives Limited

Moorfield Road Widnes
Cheshire UK WA8 3AA

Tel: +44 (0)151 495 2222 Fax: +44 (0)151 420 4401

Rockwood Clay Additives GmbH

Stadtwaldstr. 44
85368 Moosburg, Germany

Tel: +49 (0) 8761 72 150-0 Fax: +49 (0) 8761 72 150-334

Rockwood Specialties (Singapore) Pte. Limited

171 Chin Swee Road
Unit No: #10-08 San Centre Singapore 169877
Tel: +65 6532 0676 Fax: +65 6532 0502